

# SGG COOL-LITE® SKN 154/154 II

HIGH PERFORMANCE  
SOLAR CONTROL GLASS  
WITH ADVANCED THERMAL  
INSULATION PROPERTIES



BUILDING GLASS UK AND IRELAND



SAINT-GOBAIN

## SGG COOL-LITE® SKN 154/154 II

COMBINING HIGH PERFORMANCE WITH EXCELLENT NEUTRALITY, FOR OPTIMAL SOLAR CONTROL AND THERMAL EFFICIENCY

### APPLICATIONS

SGG COOL-LITE SKN 154 and SKN 154 II are two solar control coatings for use in residential or commercial buildings alike, either for façades or overhead glazing. Due to the unique properties of the coatings, they are ideally suited to applications requiring annealed and toughened or heat-strengthened glass.

### DESCRIPTION

SGG COOL-LITE SKN 154 and SKN 154 II are solar control products with high performance coatings. The coatings are applied to SGG PLANICLEAR clear float glass by cathodic sputtering under vacuum conditions.

SGG COOL-LITE SKN 154 II forms part of the ever-evolving range of 'to be toughened' neutral solar control coatings from SAINT-GOBAIN GLASS.

In order to achieve its superior thermal properties, solar control properties and neutral appearance,

SGG COOL-LITE SKN 154 II must always be toughened or heat-strengthened before assembly into a double-glazed unit (coating on face 2).

These two products are designed for use side-by-side within the same façade; SGG COOL-LITE SKN 154 in annealed form and SGG COOL-LITE SKN 154 II in toughened/heat-strengthened form.

### BENEFITS

SGG COOL-LITE SKN 154 is designed to offer exceptional solar and thermal performance:

- very low g-value of 0.28
- optimum U-value of 1.0W/m<sup>2</sup>K
- neutral appearance both in transmission and exterior reflection
- good levels of natural light transmission

SGG COOL-LITE SKN 154 can be used to improve the energy efficiency of buildings by considerably reducing overheating and the need for costly air conditioning. It is particularly suited to large areas of glazing where superior solar control performance is required whilst at the same time noticeably reducing excessive heat loss.

### RANGE

SGG COOL-LITE SKN 154 is available in 6000mm x 3210mm dimensions, in 6, 8 and 10mm thicknesses (12mm available on request) allowing for over-sized high-specification units.

### INSTRUCTIONS FOR USE

The technical performance and aesthetics of SGG COOL-LITE SKN 154 (annealed) and SGG COOL-LITE SKN 154 II (to be toughened/heat-strengthened) are identical. SGG COOL-LITE SKN 154 II can be toughened from stock enabling a quick turnaround for toughened/heat-strengthened double-glazed units. Together, these two coatings can be used to produce exciting and innovative projects within a short timescale. There is the additional advantage, therefore, of a short lead time for replacements.

### TECHNICAL SPECIFICATIONS

#### PERFORMANCE DATA

	DGU with SGG COOL-LITE SKN
Internal Pane	SGG PLANICLEAR
External Pane	SGG COOL-LITE 154/154 II
Composition in mm	6(16)6
Coating Positions	Face 2
LT	52%
LRe	19%
g-value	0.28
Shading Coefficient	0.32
U-Value in W/m <sup>2</sup> K Air	1.3
90% Argon	1.0

SGG COOL-LITE SKN 154 and SKN 154 II meet the durability requirements of class C of European standards EN 1096-1 and -2.

\* Light and solar performance according to EN 410



### Building Glass UK and Ireland

Saint-Gobain Glass UK Ltd  
Weeland Road, Eggborough  
East Riding of Yorkshire, DN14 0FD, UK  
www.saint-gobain-glass.com/uk

SGG COOL-LITE, SGG PLANICLEAR and all other devices and logos are registered trademarks of Saint-Gobain.

